

# SPORTS SURFACES

DATA SHEET

## COLORSINT

**Coloured acrylic resin based coating formulated to protect and colour cycling lanes and asphalt surfaces**

### CHARACTERISTICS

Colorsint is an acrylic resin-based coloured coating covering in water emulsion used on asphalt surfaces to produce cycling tracks, bicycle and pedestrian walkways and urban decorations. The product is abrasion resistant, weatherproof, resistant to UV radiation and to the aggressive action of fuels in general.

The main advantages of the product are:

- High resistance to lubricants
  - Available in a wide range of colours
  - Protects the asphalt surface from high and low temperatures
  - Increases the life of the asphalt surface
  - High resistance to abrasion and UV rays
  - Excellent colour stability
  - Easy laying
  - Cold laying
  - Resistance to fuels (Centro Sperimentale Stradale ANAS Spa, Reference Method: AM – GEN – M- P 0017 – PAR 6.5)
- If the coating is to be used for parking areas, please consult the Technical Office of Casali S.p.A. for more information.  
Colorsint may also be applied on cement decks but in this case please consult the Technical Office of Casali S.p.A.

### APPEARANCE

High viscosity pigmented paste.

### CHARACTERISTICS OF THE LIQUID PRODUCT

Characteristic	U.M.	Value	Tolerance
Specific weight	Kg/dm <sup>3</sup>	1,64	± 0,1
Dry mass residue	%	75	± 0,5
Dry volume residue	%	59	± 0,5
Residue at 450°C	%	61	± 0,5
Brookfield viscosity (with Brookfield viscosimeter rotor no. 6, speed 10)	mPa·s	90000	± 2000
pH	-	8	± 1

### LAYING INSTRUCTIONS

Tools	Thinner	Type of thinner	Cleaning tools
Rubber squeegee	Approx. 30 %	Water	Water

### LAYING SURFACE

The product may be applied on new or old asphalt decks, provided the same are in good condition and well compacted.

The deck should be perfectly clean, with no traces of oil, dust or grease. Different types of decks should be evaluated on a case by case basis, taking into account that it may be necessary to apply a primer. New asphalt should be allowed to cure for at least 3 - 4 weeks, to ensure partial oxidation of the surface, and then cleaned with a high-pressure washer.

**IMPORTANT:** resin surfaces are generally waterproof (non-draining), so that the deck should be sloped correctly to ensure efficient rainwater runoff and prevent pooling. Any corrections that may be required should be made before laying the final coating; if necessary, please consult Technical Office of Casali's S.p.A. for more information.

**CASALI**  
SPORT



Rev. 02/2018

# SPORTS SURFACES

COLORSINT

DATA SHEET

## CONSUMPTION

The minimum recommended coverage is 2 kg/sq.m applied in 3 coatings; 1 Kg/sq.m coating to steep the mat, and another two 0.5 Kg/sq.m. coatings. Coverage may vary according to the roughness of the deck. The recommended coverage on cement is 1,5 Kg/sq.m. in 3 coats.

## APPLICATION INSTRUCTIONS

Ambient temperature: MIN 10°C - MAX 40°C  
Ambient relative humidity: MAX 90%  
Laying surface temperature: MIN 5°C - MAX 50°C

## DRYING AT 23°C AND R.H. OF 50%

On surface	1 h
To touch	2 h
Interval between coatings	4 h

The times shown are for standard laboratory conditions. The drying times are strongly influenced by the weather; high temperatures and direct sunlight accelerate drying; shadows, low temperatures and high humidity levels delay drying. In winter the product should be laid in the warmer hours in the middle of the day. Always ensure that the previous layer has cured properly before applying a new coating.

## CHARACTERISTICS OF THE DRY PRODUCT

The product specifications are shown by ANAS S.p.A. (National Roads Authority) certificate number 2946/0876/00 dated 19/10/2000

## PACKAGING INSTRUCTIONS

Colours available	Red (102), Green (201), Dark green (202), Blue (303), Light blue (302), Grey (413), Orange (151), Violet (502), Deep blue (319), Violet (507) and other on request.
Packaging	50 kg. drums

## STORAGE INSTRUCTIONS

Storage temperature:	MIN 3°C - MAX 40°C
Stability in the original package:	12 months

## IMPORTANT INSTRUCTIONS

Do not apply the product in foggy or damp weather, or if rain or frost are forecast. Ensure that the deck is perfectly flat and resistant with the correct aggregate grading to prevent flaws on the surface. Repairs and/or filling should be carried out in accordance with the instructions of Casali S.p.A. Check for rising damp and/or infiltrations, and if necessary contact Casali S.p.A.'s Technical Office for more information.

## SAFETY STANDARDS

Please read the safety data sheet carefully before using this product.

## CERTIFICATION

ANAS S.p.A. (National Roads Authority) – Certificate number 2946/0876/00 dated 19/10/2000  
Colorsint is tested in accordance with and is compliant to standard EN 1297 ( Synthetic coverings for outdoor sports areas - Method of artificial ageing by long term exposure to the combination of UV radiation, elevated temperature and water.

*The data provided by these data sheets are approximate and the Company reserves the right to modify the same for technical reasons, without prior notice. The solutions proposed do not represent all the possible uses but are merely case studies deriving from Casali's installation experience and are therefore intended only for purposes of illustration. The user is exclusively responsible for the way the products illustrated are used, whether properly or improperly, for evaluating in advance the suitability or otherwise of the product for its requirements and exerting the utmost caution in handling chemical products. **Important: to ensure best colour uniformity of surface laid products, we recommend that you use materials from the same production lot as finishing layer. The Technical Office of Casali's Synthetics Division is at your complete disposal for any further specific information or explanations you may require (phone 071 9162095).***

**CASALI**  
SPORT



Rev. 02/2018