

SPORTS SURFACES

DATA SHEET

TOP SG

**Finish of the Supersoft SG system
synthetic resin based coating in water emulsion**

CHARACTERISTICS

Top SG is a synthetic resin based coating in water emulsion completely free of sand used as finish coating on Supersoft SG system for wheelchair sports. Its special formulation with hard resins allow to reach the perfect level of resistance and duration of the finish layer and the absence of sand give to the surface the right level of grip during the transition of wheelchair.

APPEARANCE

Pigmented medium viscosity liquid

CHARACTERISTICS OF THE LIQUID PRODUCT

Characteristic	U.M.	Value	Tolerance
Specific weight	Kg/dm ³	1,2	± 0,1
Dry mass residue	%	56	± 0,5
Dry volume residue	%	47	± 0,5
Residue at 450°C	%	24	± 0,5
Brookfield viscosity (with Brookfield viscosimeter rotor no. 4, speed 5)	mPa·s	18000	± 2000
pH	-	8	± 1

LAYING INSTRUCTIONS

Tools	Thinner	Type of thinner	Cleaning tools
Rubber squeegee	15-20%	Water	Water

LAYING SURFACE

Surface already treated with Supersoft.

IMPORTANT: resin surfaces are generally waterproof (non-draining) so that the deck must be sloped correctly to ensure rainwater runoff and prevent pooling. Works to correct the deck must be carried out before laying the final covering; if necessary please contact the Technical Office of Casali S.p.A.

CONSUMPTION

The minimum recommended consumption is 0,25 Kg/sq.m. in 1 coat.

APPLICATION INSTRUCTIONS

Ambient temperature: MIN 10°C - MAX 40°C

Ambient relative humidity: MAX 90 %

Laying surface temperature: MIN 5°C - MAX 50°C

CASALI
SPORT



Rev. 11/2018

SPORTS SURFACES

TOP SG

DATA SHEET

DRYING AT 23°C AND R.H. OF 50%

On surface 30 min

To touch 1 h

Interval between coatings 2 h

The times indicated refer to standard laboratory conditions. Curing times are strongly affected by weather conditions; high temperatures and direct sunlight accelerate curing; shade, low temperatures and high levels of humidity slow down curing. In winter, lay the product in the warmer hours of the day. Always allow the coating to dry perfectly before applying the next coating.

PACKAGING INSTRUCTIONS

Colours available Red (102), Green (201), Dark green (202), Blue (303), Light blue (302), Grey (413), Orange (151), Violet (502), Deep blue (319), Violet (507) and other on request.

Packaging 18 Kg plastic drums

STORAGE INSTRUCTIONS

Storage temperature: MIN 3°C - MAX 40°C

Stability in the original package: 12 months

IMPORTANT INSTRUCTIONS

Do not apply the product in the case of fog, high humidity levels, rain or frost. The conditions of the deck must be checked to ensure that it is plane, resistant, consistent that the granule grading is correct in order to prevent imperfections on the surface. Repairs and/or filling must be carried out according to the specifications of Casali S.p.A. Check for rising dampness and/or infiltrations, if necessary contact the Technical Office of Casali S.p.A.

SAFETY STANDARDS

Please read the safety data sheet carefully before using this product.

*The data provided by these data sheets are approximate and the Company reserves the right to modify the same for technical reasons, without prior notice. The solutions proposed do not represent all the possible uses but are merely case studies deriving from Casali's installation experience and are therefore intended only for purposes of illustration. The user is exclusively responsible for the way the products illustrated are used, whether properly or improperly, for evaluating in advance the suitability or otherwise of the product for its requirements and exerting the utmost caution in handling chemical products. **Important: to ensure best colour uniformity of surface laid products, we recommend that you use materials from the same production lot as finishing layer. The Technical Office of Casali's Synthetics Division is at your complete disposal for any further specific information or explanations you may require (phone 071 9162095).***

CASALI
SPORT



Rev. 11/2018