

# SPORTS SURFACES

DATA SHEET

## SUPERSOFT EVOLUTION HD

2<sup>nd</sup> elastic layer of the Supersoft Pro Turf System

### CHARACTERISTICS

Supersoft Evolution HD is an elastic connecting layer between Supersoft Evolution and Supersoft Pro of the Supersoft Pro Turf system. Just the correct mixture of rubber granules and quartz sand complete the elastic effect of the previous layer ensuring an excellent finish. The Supersoft Pro Turf system is tested by the ITF (International Tennis Federation) in Speed Class 3 (medium).

### APPEARANCE

Black high-viscosity paste.

### CHARACTERISTICS OF THE LIQUID PRODUCT

Characteristic	U.M.	Value	Tolerance
Specific weight	Kg/dm <sup>3</sup>	1,47	± 0,05
Dry mass residue	%	74	± 3
Dry volume residue	%	62	± 3
Residue at 450°C	%	49	± 3
Brookfield viscosity (with Brookfield viscosimeter rotor no. 6, speed 6)	mPa·s	160000	± 20000
pH	-	8	± 1

### LAYING INSTRUCTIONS

Tools	Thinner	Type of thinner	Cleaning tools
Rubber spatula	25-30%	Water	Water

### LAYING SURFACE

The deck consists of a compact well-levelled layer of Supersoft Evolution; sand the deck only after applying the coating of Supersoft Evolution HD. **IMPORTANT:** resin surfaces are generally waterproof (non-draining) so that the deck must be sloped correctly to ensure rainwater runoff and prevent pooling. Works to correct the deck must be carried out before laying the final covering; if necessary please contact the Technical Office of Casali S.p.A.

### CONSUMPTION

Apply at least 1.5 Kg./sq.m. undiluted product in two coatings, crossing the coatings if possible.

### APPLICATION INSTRUCTIONS

Ambient temperature: MIN 10°C - MAX 40°C  
Ambient relative humidity: MAX 90 %  
Laying surface temperature: MIN 5°C - MAX 50°C

# SPORTS SURFACES

## SUPERSOFT EVOLUTION HD

DATA SHEET

### DRYING AT 23°C AND R.H. OF 50%

On surface	1 h
To touch	2 h
Interval between coatings	4 h

The times indicated refer to standard laboratory conditions. Curing times are strongly affected by weather conditions; high temperatures and direct sunlight accelerate curing; shade, low temperatures and high levels of humidity slow down curing. In winter, lay the product in the warmer hours of the day. Always allow the coating to dry perfectly before applying the next coating.

### PACKAGING INSTRUCTIONS

Colours available	Black.
Packaging	40 kg. drums

### STORAGE INSTRUCTIONS

Storage temperature:	MIN 3°C - MAX 50°C
Stability in the original package:	12 months

### IMPORTANT INSTRUCTIONS

Do not apply the product in the case of fog, high humidity levels, rain or frost. The conditions of the deck must be checked to ensure that it is plane, resistant, consistent that the granule grading is correct in order to prevent imperfections on the surface. Repairs and/or filling must be carried out according to the specifications of Casali S.p.A. Check for rising dampness and/or infiltrations, if necessary contact the Technical Office of Casali S.p.A.

### SAFETY STANDARDS

Please read the safety data sheet carefully before using this product.

### CERTIFICATION

All material - in perfect accordance with the Minimum Environmental Criteria (CAM) standards and the "Waste Hierarchy Principle" that rewards prevention in the production of waste itself - is packaged in 100% recyclable metal drums. Due to the packaging of the resin formulation inside plastic bags, these drums remain completely clean at the end of the product's use and therefore, as opposed to the usual plastic containers, entirely recyclable. This reduces the production of plastic packaging and packaging waste by more than 94%, significantly reducing the loading, transport and delivery of these non-recyclable materials to authorised PPWDs.

*The data provided by these data sheets are approximate and the Company reserves the right to modify the same for technical reasons, without prior notice. The solutions proposed do not represent all the possible uses but are merely case studies deriving from Casali's installation experience and are therefore intended only for purposes of illustration. The user is exclusively responsible for the way the products illustrated are used, whether properly or improperly, for evaluating in advance the suitability or otherwise of the product for its requirements and exerting the utmost caution in handling chemical products. **Important: to ensure best colour uniformity of surface laid products, we recommend that you use materials from the same production lot as finishing layer. The Technical Office of Casali's Synthetics Division is at your complete disposal for any further specific information or explanations you may require (phone 071 9162095).***

**CASALI**  
SPORT



Rev. 11/2024