

## TOP SG

**Finish of the Supersoft SG system  
synthetic resin based coating in water emulsion**

## CHARACTERISTICS

Top SG is a sythetic resin based coating in water emulsion completely free of sand used as finish coating on Supersoft SG system for wheelchair sports. His special formulation with hard resins allow to reach the perfect level of resistance and duration of the finish layer and the absence of sand give to the surface the right level of grip during the transition of wheelchair.

## APPEARANCE

Pigmented medium viscosity liquid

## CHARACTERISTICS OF THE LIQUID PRODUCT

| Characteristic   | U.M.               | Value | Tolerance |
|--|--------------------|-------|-----------|
| Specific weight  | Kg/dm <sup>3</sup> | 1,2   | ± 0,1     |
| Dry mass residue   | %                  | 56    | ± 0,5     |
| Dry volume residue   | %                  | 47    | ± 0,5     |
| Residue at 450°C   | %                  | 24    | ± 0,5     |
| Brookfield viscosity (with Brookfield viscosimeter rotor no. 4, speed 5) | mPa·s              | 18000 | ± 2000    |
| pH   | -                  | 8     | ± 1       |

## LAYING INSTRUCTIONS

| Tools           | Thinner | Type of thinner | Cleaning tools |
|-----------------|---------|-----------------|----------------|
| Rubber squeegee | 15-20%  | Water           | Water          |

## LAYING SURFACE

Surface already treated with Supersoft.

IMPORTANT: resin surfaces are generally waterproof (non-draining) so that the deck must be sloped correctly to ensure rainwater runoff and prevent pooling. Works to correct the deck must be carried out before laying the final covering; if necessary please contact the Technical Office of Casali S.p.A.

## CONSUMPTION

The minimum recommended consumption is 0,25 Kg/sq.m. in 1 coat.

## APPLICATION INSTRUCTIONS

Ambient temperature: MIN 10°C - MAX 40°C

Ambient relative humidity: MAX 90 %

Laying surface temperature: MIN 5°C - MAX 50°C

**DRYING AT 23°C AND R.H. OF 50%**

|                                  |        |
|----------------------------------|--------|
| <b>On surface</b>                | 30 min |
| <b>To touch</b>                  | 1 h    |
| <b>Interval between coatings</b> | 2 h    |

The times indicated refer to standard laboratory conditions. Curing times are strongly affected by weather conditions; high temperatures and direct sunlight accelerate curing; shade, low temperatures and high levels of humidity slow down curing. In winter, lay the product in the warmer hours of the day. Always allow the coating to dry perfectly before applying the next coating.

**PACKAGING INSTRUCTIONS**

|                          |   |
|--------------------------|---|
| <b>Colours available</b> | Red (102), Green (201), Dark green (202), Blue (303), Light blue (302), Grey (413), Orange (151), Violet (502), Deep blue (319), Violet (507) and other on request. |
| <b>Packaging</b>         | 18 Kg plastic drums   |

**STORAGE INSTRUCTIONS**

|   |                    |
|---|--------------------|
| <b>Storage temperature:</b>               | MIN 3°C - MAX 40°C |
| <b>Stability in the original package:</b> | 12 months          |

**IMPORTANT INSTRUCTIONS**

Do not apply the product in the case of fog, high humidity levels, rain or frost. The conditions of the deck must be checked to ensure that it is plane, resistant, consistent that the granule grading is correct in order to prevent imperfections on the surface. Repairs and/or filling must be carried out according to the specifications of Casali S.p.A. Check for rising dampness and/or infiltrations, if necessary contact the Technical Office of Casali S.p.A.

**SAFETY STANDARDS**

Please read the safety data sheet carefully before using this product.

**CERTIFICATION**

Top SG is tested in accordance with and is compliant to standard EN 1297 (Synthetic coverings for outdoor sports areas - Method of artificial ageing by long term exposure to the combination of UV radiation, elevated temperature and water).

All standard colours contribute effectively to the containment of the heat barrier effect (CAM/GPP-EC Decree) by achieving SRI (Solar Reflect Index) >29. Please consult the Casali S.p.A. technical department for the data of the individual colours.

All material - in perfect accordance with the Minimum Environmental Criteria (CAM) standards and the "Waste Hierarchy Principle" that rewards prevention in the production of waste itself - is packaged in 100% recyclable metal drums. Due to the packaging of the resin formulation inside plastic bags, these drums remain completely clean at the end of the product's use and therefore, as opposed to the usual plastic containers, entirely recyclable. This reduces the production of plastic packaging and packaging waste by more than 94%, significantly reducing the loading, transport and delivery of these non-recyclable materials to authorised PPWDs.

*The data provided by these data sheets are approximate and the Company reserves the right to modify the same for technical reasons, without prior notice. The solutions proposed do not represent all the possible uses but are merely case studies deriving from Casali's installation experience and are therefore intended only for purposes of illustration. The user is exclusively responsible for the way the products illustrated are used, whether properly or improperly, for evaluating in advance the suitability or otherwise of the product for its requirements and exerting the utmost caution in handling chemical products. **Important: to ensure best colour uniformity of surface laid products, we recommend that you use materials from the same production lot as finishing layer. The Technical Office of Casali's Synthetics Division is at your complete disposal for any further specific information or explanations you may require (phone 071 9162095).***