SPORTS SURFACES

SUPERSOFT WS

Concentrated coloured acrylic resin based coating for tennis courts

CHARACTERISTICS

Supersoft WS is a concentrated coloured acrylic resin based coating in water emulsion especially formulated for tennis courts. Supersoft WS contains pigments that are highly resistant to ultraviolet radiation, elastic resins and the addition of selected quartz sands, to ensure exceptional playing comfort and resistance. The Supersoft system is tested by the ITF (International Tennis Federation) in playing Speed Class 4 (medium fast).

APPEARANCE

Pigmented high-viscosity paste.

CHARACTERISTICS OF THE LIQUID PRODUCT			
Characteristic	U.M.	Value	Tolerance
Specific weight	Kg/dm³	1,24	± 0,1
Dry mass residue	%	52	± 3
Dry volume residue	%	42	± 3
Residue at 450°C	%	26	± 3
Brookfield viscosity (with Brookfield viscosimeter rotor no. 6, speed 20)	mPa·s	30000	± 3000
рН	-	8	± 1

APPLICATION METHOD

Add quartz sand (type 0.1 - 0.3 mm selected and dried) and clean water (approx. 30% of the total weight of the mixture), mixing slowly. Continue until the mixture is perfectly uniform. The mixture may be mixed by hand or in a cement mixer. Apply 3 coatings in the following Supersoft WS / quartz sand weight ratio.

FIRST COATING = 50:50

FIRST COATING = 50:50 SECOND COATING = 50:50 THIRD COATING = 50:50

For a slightly smoother finish, apply the last layer with a mixing ratio of Supersoft WS / quartz sand = 60:40

LAYING INSTRUCTIONS				
Tools	Thinner	Type of thinner	Cleaning tools	
Rubber spatula	Approx. 30 % of the total mixture (resin + sand)	Water	Water	

LAYING SURFACE

Supersoft WS is developed above all for asphalt decks (see deck preparation instructions) following pre-treatment with Softbase WS; for application on cement deck please consult the Technical Office of Casali S.p.A.

IMPORTANT: resin surfaces are generally waterproof (non-draining) so that the deck must be sloped correctly to ensure rainwater runoff and prevent pooling. Works to correct the deck must be carried out before laying the final covering; if necessary please contact the Technical Office of Casali S.p.A.





Rev. 02/2018

SPORTS SURFACES

SUPERSOFT WS

CONSUMPTION

The recommended coverage on bitumen mat soaked with Softbase is at least 0.75 Kg./sq.m. of Supersoft WS + 0.75 Kg./sq.m. of sand applied in 3 coatings (0.25 Kg./sq.m. of Supersoft WS + 0.25 Kg./sq.m. of sand per coating).

APPLICATION INSTRUCTIONS

Ambient temperature: MIN 10°C - MAX 40°C Ambient relative humidity: MAX 90 % Laying surface temperature: MIN 5°C - MAX 50°C

DRYING AT 23°C AND R.H. OF 50%

On surface	1 h
To touch	2 h
Interval between coatings	4 h

The times indicated refer to standard laboratory conditions. Curing times are strongly affected by weather conditions; high temperatures and direct sunlight accelerate curing; shade, low temperatures and high levels of humidity slow down curing. In winter, lay the product in the warmer hours of the day. Always allow the coating to dry perfectly before applying the next coating.

PACKAGING INSTRUCTIONS

Colours available Red (102), Green (201), Dark green (202), Blue (303), Light blue (302), Grey (413), Orange (151), Violet (502) Deep blue (319), Violet (507), Red clay (113) and other on request.	
Packaging	40 kg. drums.

STORAGE INSTRUCTIONS

Storage temperature:	MIN 3°C - MAX 40°C
Stability in the original package:	12 months

IMPORTANT INSTRUCTIONS

Do not apply the product in the case of fog, high humidity levels, rain or frost. The conditions of the deck must be checked to ensure that it is plane, resistant, consistent that the granule grading is correct in order to prevent imperfections on the surface. Repairs and/or filling must be carried out according to the specifications of Casali S.p.A. Check for rising dampness and/or infiltrations, if necessary contact the Technical Office of Casali S.p.A.

SAFETY STANDARDS

Please read the safety data sheet carefully before using this product.

CERTIFICATION

Supersoft WS is tested in accordance with and is compliant to standard EN 1297 (Synthetic coverings for outdoor sports areas - Method of artificial ageing by long term exposure to the combination of UV radiation, elevated temperature and water).

The data provided by these data sheets are approximate and the Company reserves the right to modify the same for technical reasons, without prior notice. The solutions proposed do not represent all the possible uses but are merely case studies deriving from Casali's installation experience and are therefore intended only for purposes of illustration. The user is exclusively responsible for the way the products illustrated are used, whether properly or improperly, for evaluating in advance the suitability or otherwise of the product for its requirements and exerting the utmost caution in handling chemical products. Important: to ensure best colour uniformity of surface laid products, we recommend that you use materials from the same production lot as finishing layer. The Technical Office of Casali's Synthetics Division is at your complete disposal for any further specific information or explanations you may require (phone 071 9162095).





Rev. 02/2018