SPORTS SURFACES

SUPERSOFT EVOLUTION

1st elastic layer of the Supersoft Pro Turf System

CHARACTERISTICS

Supersoft Evolution is the first rubber granule layer of the Supersoft Pro Turf system. Select rubber granules and special binders give this product just the right elasticity and resistance. The Supersoft Pro Turf system is tested by the ITF (International Tennis Federation) in Speed Class 3 (medium).

APPEARANCE

Component A: black thixotropic paste. Component B: straw yellow liquid.

CHARACTERISTICS OF THE LIQUID PRODUCT				
Characteristic	U.M.	Value	Tolerance	
Specific weight	Kg/dm³	1,04	± 0,05	
Dry mass residue	%	55	± 3	
Dry volume residue	%	54	± 3	
Brookfield viscosity (with Brookfield viscosimeter rotor no. 6, speed 6)	mPa·s	78000	± 2000	
рН	-	8	± 1	

APPLICATION METHOD

A 3 litre drum of additive (Additive SE) is supplied with each 30 kg. drum of product, which is first dispersed in the water used for thinning. To dilute, first mix the additive into the water with a hand mixer, then add the mixture to Supersoft Evolution mixing with a hand or cement mixer until the mixture is prefect smooth and liquid.

LAYING INSTRUCTIONS			
Toolings	Thinner	Type of thinner	Cleaning tools
Rubber spatula	35 - 40 %	Water	Water

LAYING SURFACE

Supersoft Evolution should preferably be used on asphalt decks (please read the instructions provided on how to prepare the deck) after treating the deck with Softbase; if the product is applied on a concrete deck, contact the Technical Office of Casali S.p.A. for more information. IMPORTANT: resin surfaces are generally waterproof (non-draining) so that the deck must be sloped correctly to ensure rainwater runoff and prevent pooling. Works to correct the deck must be carried out before laying the final covering; if necessary please contact the Technical Office of Casali S.p.A.

CONSUMPTION

Minimum recommended coverage of product on bituminous mat treated with Softbase is 1.8 - 2 kg/sq.m. applied in 2 crossed coatings.





Rev. 02/2018

SPORTS SURFACES

SUPERSOFT EVOLUTION

APPLICATION INSTRUCTIONS

Ambient temperature: MIN 10°C - MAX 40°C Ambient relative humidity: MAX 90 % Laying surface temperature: MIN 5°C - MAX 50°C

DRYING AT 23°C AND R.H. OF 50% On surface 2 h To touch 4 h Interval between coatings 8 h

The times indicated refer to standard laboratory conditions. Curing times are strongly affected by weather conditions; high temperatures and direct sunlight accelerate curing; shade, low temperatures and high levels of humidity slow down curing. In winter, lay the product in the warmer hours of the day. Always allow the coating to dry perfectly before applying the next coating.

PACKAGING INSTRUCTIONS		
Colours available	Balck.	
Packaging	30 kg. drums + additive SE	

STORAGE INSTRUCTIONS		
Storage temperature:	MIN 3°C - MAX 40°C	
Stability in the original package:	12 months	

IMPORTANT INSTRUCTIONS

Do not apply the product in the case of fog, high humidity levels, rain or frost. The conditions of the deck must be checked to ensure that it is plane, resistant, consistent that the granule grading is correct in order to prevent imperfections on the surface. Repairs and/or filling must be carried out according to the specifications of Casali S.p.A. Check for rising dampness and/or infiltrations, if necessary contact the Technical Office of Casali S.p.A.

SAFETY STANDARDS

Please read the safety data sheet carefully before using this product.

The data provided by these data sheets are approximate and the Company reserves the right to modify the same for technical reasons, without prior notice. The solutions proposed do not represent all the possible uses but are merely case studies deriving from Casali's installation experience and are therefore intended only for purposes of illustration. The user is exclusively responsible for the way the products illustrated are used, whether properly or improperly, for evaluating in advance the suitability or otherwise of the product for its requirements and exerting the utmost caution in handling chemical products. Important: to ensure best colour uniformity of surface laid products, we recommend that you use materials from the same production lot as finishing layer. The Technical Office of Casali's Synthetics Division is at your complete disposal for any further specific information or explanations you may require (phone 071 9162095).





Rev. 02/2018